

Solar Greyback Frontlit Premium

SL-F04

Soyang's innovative eco range: PVC-Free. Low-emission.
Oekotex Standard 100 Certificated.

BRIEF DESCRIPTION

- PA-coated, 1000x1000, 20x20 base fabric with grey back
- 100% opacity, better strength
- Can be used as banner material both indoors and outdoors

FEATURES



PVC-FREE



PHTHALATE FREE



FULL OPACITY



FIRE-RESISTANT

INK PRINTABILITY



UV



LATEX



SOL



ECO SOL

MATERIAL DETAILS

| PROPERTIES | TEST METHOD | METRIC | IMPERIAL |
|---------------------|--|---|------------------|
| Total Weight | DIN EN ISO 2286-2, ASTM D751 | 330 g/sq.m | 9.7 oz/sq.yd |
| Base Fabric | DIN 60001, ASTM D7641 | Polyester | Polyester |
| Yarn Dtex | DIN EN ISO 2060, ASTM D 1907 | 1100x1100 dtex | 1000x1000 denier |
| Shielding Rate | ANSI PH2.19, ISO 5/2 | 100% | |
| Tensile Strength | DIN EN ISO 1421 | 2490x2230 N/5cm | 285x255 lbs/inch |
| Tear Strength | DIN 53363 | 530x490 N | 119x110 lbs |
| Flame Resistance | DIN 4102-1-B1, NFPA 701 Test1, EN13501-1 | DIN 4102-1-B1, NFPA 701 Test1, EN13501-1 | |
| Width Available | DIN EN ISO 3759, ASTM D751-2006 | Max 500cm | 197" |
| Standard Length | DIN EN ISO 3759, ASTM D751-2006 | 50m | 55yds |
| Storage Temperature | | 10 ~40°C | 39~89°F |
| Storage Humidity | | 10~70%RH | |
| Shelf Life | | 12 months at recommended storage temperature and humidity | |

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.